


FAG

HS7016-E-T-P4S-UL

High speed spindle bearing

High speed spindle bearing HS70...-E,
adjusted, in pairs or sets, contact angle $\alpha = 25^\circ$, restricted tolerances

Informacje techniczne





Twoja aktualna wersja produktu

Contact angle	E	Contact angle 25°
Sealing	Without	Not sealed
Cage	T	Laminated fabric cage
Tolerance class	P4S	Tolerance class P4S, FAG standard better than P4 to ISO 492:2023
Arrangement bearing set	U	Single bearing
Preload class	L	Preload light

Main Dimensions & Performance Data

d	80 mm	Bore diameter
D	125 mm	Outside diameter
B	22 mm	Width
C _r	28.500 N	Basic dynamic load rating, radial
C _{0r}	20.600 N	Basic static load rating, radial
C _{ur}	2.160 N	Fatigue load limit, radial
n _G Grease	14.000 1/min	Limiting speed for grease lubrication
n _G Oil	22.000 1/min	Limiting speed for oil lubrication
n _G	22.000 1/min	Limiting speed
≈m	0,886 kg	Masa





Mounting dimensions

d _a	88 mm	Diameter shaft shoulder
d _a	h12	Diameter shaft shoulder clearance
D _a	117 mm	Shoulder diameter outer ring
D _a	H12	Shoulder diameter outer ring clearance
r _a max	1 mm	Maximum recess radius
r _{a1} max	0,6 mm	Maximum recess radius
E _{tk} min	97,3 mm	Minimum diameter injection pitch
E _{tk} max	99,7 mm	Maximum diameter injection pitch
E _{tk1} min	94 mm	Minimum diameter injection pitch
E _{tk1} max	99,7 mm	Maximum diameter injection pitch
a	34,9 mm	Distance between the apexes of the pressure cones

Dimensions

r _{min}	1,1 mm	Minimum chamfer dimension
r ₁ min	1,1 mm	Minimum chamfer dimension
α	25 °	Contact angle

Temperature range

T _{min}	-30 °C	Operating temperature min.
T _{max}	100 °C	Operating temperature max.



Additional information

F_{VL}	173 N	Preload force light
F_{VM}	518 N	Preload force medium
F_{VH}	1.035 N	Preload force heavy
K_{aEL}	497 N	Lift-off force light
K_{aEM}	1.521 N	Lift-off force medium
K_{aEH}	3.103 N	Lift-off force heavy
c_{aL}	148 N/ μ m	Axial rigidity light
c_{aM}	220 N/ μ m	Axial rigidity medium
c_{aH}	286 N/ μ m	Axial rigidity heavy

Właściwości

- 

Obciążenie promieniowe
- 

Obciążenie osiowe jednokierunkowe
- 

Smarowanie smarem
- 

Smarowanie olejem
- 

Bez uszczelnienia