


FAG

HS7022-C-T-P4S-UL

High speed spindle bearing

High speed spindle bearing HS70...-C, adjusted, in pairs or sets, contact angle $\alpha = 15^\circ$, restricted tolerances

Informacje techniczne





Twoja aktualna wersja produktu

Contact angle	C	Contact angle 15°
Sealing	Without	Not sealed
Cage	T	Laminated fabric cage
Tolerance class	P4S	Tolerance class P4S, FAG standard better than P4 to ISO 492:2023
Arrangement bearing set	U	Single bearing
Preload class	L	Preload light

Main Dimensions & Performance Data

d	110 mm	Bore diameter
D	170 mm	Outside diameter
B	28 mm	Width
C _r	48.000 N	Basic dynamic load rating, radial
C _{0r}	38.000 N	Basic static load rating, radial
C _{ur}	3.400 N	Fatigue load limit, radial
n _G Grease	12.000 1/min	Limiting speed for grease lubrication
n _G Oil	18.000 1/min	Limiting speed for oil lubrication
n _G	18.000 1/min	Limiting speed
≈m	2,076 kg	Masa





Mounting dimensions

d _a	121 mm	Diameter shaft shoulder
d _a	h12	Diameter shaft shoulder clearance
D _a	159 mm	Shoulder diameter outer ring
D _a	H12	Shoulder diameter outer ring clearance
r _a max	2 mm	Maximum recess radius
r _{a1} max	1 mm	Maximum recess radius
E _{tk} min	133,3 mm	Minimum diameter injection pitch
E _{tk} max	136,5 mm	Maximum diameter injection pitch
E _{tk1} min	129,2 mm	Minimum diameter injection pitch
E _{tk1} max	136,5 mm	Maximum diameter injection pitch
a	32,8 mm	Distance between the apexes of the pressure cones

Dimensions

r _{min}	2 mm	Minimum chamfer dimension
r _{1 min}	2 mm	Minimum chamfer dimension
α	15 °	Contact angle

Temperature range

T _{min}	-30 °C	Operating temperature min.
T _{max}	100 °C	Operating temperature max.



Additional information

F_{VL}	168 N	Preload force light
F_{VM}	503 N	Preload force medium
F_{VH}	1.005 N	Preload force heavy
K_{aEL}	499 N	Lift-off force light
K_{aEM}	1.566 N	Lift-off force medium
K_{aEH}	3.257 N	Lift-off force heavy
c_{aL}	77 N/μm	Axial rigidity light
c_{aM}	121 N/μm	Axial rigidity medium
c_{aH}	164 N/μm	Axial rigidity heavy

Właściwości

- 

Obciążenie promieniowe
- 

Obciążenie osiowe jednokierunkowe
- 

Smarowanie smarem
- 

Smarowanie olejem
- 

Bez uszczelnienia